U.S. DEPARTMENT OF COMMERCE
National Technical Information Service

PB-269 316

Particle Size of Home and Garden Pesticides Containing Fungicides

Environmental Protection Agency, Corvallis, Oreg

Jun 77

EPA-540/9-77-015

PB 269 316

PARTICLE SIZE OF HOME AND GARDEN PESTICIDES CONTAINING FUNGICIDES

JUNE 1977

U.S. Environmental Protection Agency
Washington, D. C. 20460

DEPARTMENT OF COMMERCE
NATIONAL TECHNICAL
INFORMATION SERVICE
SPRINGFIELD, VA. 22161

BIBLIOGRAPHIC DATA SHEET	EPA-540/9-77-011	

4. Title and Subtitle: **Particle Size of Home and Garden Pesticides Containing Fungicides**

5. Report Date: **June 1977**

7. Author(s): **H.L. Dooley**

9. Performing Organization Name and Address: **Northwest Biological Investigations Station, Technical Services Division, U.S. Environmental Protection Agency, 1320 Orchard Ave., Corvallis, Oregon 97330**

12. Sponsoring Organization Name and Address: **EPA, Office of Pesticide Programs, Technical Services Division, Washington, D.C. 20460**

13. Type of Report & Period Covered

14. FIFRA/NL

15. Supplementary Notes

16. Abstracts

Nineteen different commercial home and garden pesticide formulations containing fungicides from 17 manufacturers were evaluated for particle size by wet- and dry-sieve methods. Significantly different results were obtained by each method. The wet-sieved method showed that at least 90% of the particles were smaller than 75 µm in 17 formulations, while the dry-sieved method indicated that 70% of the particles were smaller than 75 µm in only seven formulations. The dry sieving method was found to be most appropriate for the evaluation of dusts. The mean particle size of most currently marketed commercial pesticide dusts for home and garden use is 149 µm or smaller.

17. Key Words and Document Analysis. 17a. Descriptors

pesticide formulations
home and garden
fungicides
particle size
wet-sieve method
dry-sieve method
dusts
insecticides
Folpet
Folpet plus sulfur
Chlorothalonil plus Karathane
zinc salts
copper zinc chromate complex

17b. Identifiers/Open-Ended Terms

17c. COSATI Field/Group

18. Availability Statement

19. Security Class (This Report)

20. Security Class (This Page)

21. No. of Pages

22. Price

PB-264 126

PARTICLE SIZE OF HOME AND GARDEN PESTICIDES CONTAINING FUNGICIDES

H. L. Dooley

Northwest Biological Investigations Station, Technical Services Division, U. S. Environmental Protection Agency, 3320 Orchard Avenue, Corvallis, Oregon 97330

June 1977

EPA-540/9-77-015

PARTICLE SIZE OF HOME AND GARDEN PESTICIDES CONTAINING FUNGICIDES

H. L. Bowley

ABSTRACT

Nineteen different commercial home and garden pesticide formulations containing fungicides from 17 manufacturers were evaluated for particle size by wet- and dry-sieve methods. Significantly different results were obtained by each method. The wet-sieved method showed that at least 90% of the particles were smaller than 75 µm in 17 formulations, while the dry-sieved method indicated that 70% of the particles were smaller than 75 µm in only seven formulations. The dry sieving method was found to be most appropriate for the evaluation of dusts. The mean particle size of most currently marketed commercial pesticide dusts for home and garden use is 149 µm or smaller.

The relationship between particle size and pesticide effectiveness is well known (4, 5, 6, 7, 8, 9, 10). Pesticide manufacturers frequently specify the portion of their product that will pass a 325-mesh sieve (i.e. 44 µm). Methods for particle size determination vary among manufacturers, but wet and dry sieving are most common (1, 2).

The work reported here was undertaken to determine the particle size of commercially available home and garden pesticide dusts containing fungicides and to compare the two methods used for determining size.

MATERIALS AND METHODS

Home and garden pesticide formulations often contain both fungicides and insecticides. Fungicidal components involved in this study were: Folpet, Folpet plus sulfur, Chlorothalonil plus Karathane, zinc salts, and a copper zinc chromate complex. A sulfur compound and a copper zinc chromate complex were the only products that did not contain insecticides in their formulation.

Both dry- and wet-sieving (1, 2) methods were evaluated in this study. Nineteen pesticide dust formulations registered for domestic use, including 60 different samples collected from 17 distributors, were sieved using both methods.

Dry sieving: Three aliquots containing 10 g each of each pesticide formulation were independently dry sieved through a nest of Tyler standard sieves consisting of 149, 74, and 44 µm openings (100, 200, and 325-meshes per inch). The samples were placed on the top sieve (149 µm) and the nest was shaken for 10 minutes on a model RX02 Tyler Portable Sieve Shaker. Dust remaining on each sieve and in the bottom pan was weighed at the conclusion of the shake cycle and the mean percent weight of the material on each sieve was calculated.

Wet sieving: Three aliquots containing 10 g each of each pesticide formulation were independently wet sieved through a nest of Tyler standard sieves consisting of 149, 74, and 44 µm openings (100, 200, and 325-meshes per inch). The sieves were thoroughly wet with tap water before the sample was placed on the upper sieve of the nest. Then the sample was washed through the sieves with a continuous stream of tap water (about 1100-1200 ml/minute). Samples were considered completely sieved when the water passing the 44 µm sieve was clear. Material retained on each sieve was individually washed into a separate petri dish and the uncovered dishes were placed in a drying oven at 27 C for 24 hours. After cooling, weights of the pesticide formulation were determined and the mean percent weight of material on each sieve was calculated.

RESULTS AND DISCUSSION

The percentage of each dust retained on 100, 200, and 325-mesh sieves and the percentage that passed the 325-mesh sieve were expressed as particle size groups based on sieving behavior (Table 1). More than 70% of the particles in formulations A, B, C (Folpet), H (Folpet plus sulfur), J (Captan), F (sulfur), and Q (Karathane plus Chlorothalonil) were smaller than 75 µm as determined by the dry-sieve method. However, more than 90% of the particles of 17 wet-sieved formulations contained particles smaller than 75 µm. Formulations L (Captan), R (copper zinc chromate), and S (zinc salts) contained the majority of particles larger than 149 µm by the dry-sieve method. Eighty percent of the particles from Folpet (A), Captan (J and L), and sulfur (F) formulations measured less than 45 µm in size when tested by the wet-sieve technique.

The particle size distribution of similar dry-sieved formulations was often distinctly different. For example, in one Captan formulation (J) less than 1% of the particles were greater than 150 µm but in a similar formulation (L) over 70% of the particles were larger than 150 µm. A similar disparity of particle size distribution occurred with two similar Folpet formulations (A vs. B).

Smaller particles may cause over-application when used in plastic squeeze dusters (3). It is difficult to achieve uniform coverage with these dusters when the dust formulation is principally composed of small particle sizes. For example, with formulation A approximately 2.8 times as much dust was applied as when plants were dusted with similar formulation G. Formulations which contain smaller particles may result in over application and reduce photosynthesis of the leaves

unless the excess dust is removed following application. Larger particles applied with plastic squeeze dusters may result in poor distribution of the dust on the leaf surface if the duster orifice becomes clogged.

Particle size affects applicator effectiveness. This work demonstrates that the method by which particle size is determined is an important factor in achieving desired results. Because dusts are applied dry, the most appropriate method of evaluation is dry sieving. Both the wet- and dry-sieving methods are necessary to determine particle size of products which may be used as dusts or sprays.

Significant differences between aliquots did not exist and consistent results were obtained using both methods.

The amount of pesticide formulation to be sieved is important. Ten grams of material can be sieved without overloading the sieves. Therefore, 10 gram aliquots were used.

Material may be effectively sieved in 10 minutes provided that only three sieves are used.

Samples containing Folpet as the only fungicide ingredient were from different manufacturers (except F and F). All other samples containing the same fungicide component were from different manufacturers. The results illustrate that various manufacturers strive for different particle size ranges or have poor quality control. Some manufacturers may blend fungicides and insecticides of different particle sizes to prepare combination products.

Particle size is not regulated unless specified on the product label but can be an important factor in product effectiveness.

Table 1. Particle size distribution of pesticide dusts determined by dry and wet sieving.

Sample designation	No. of samples tested	Pesticide: Fungicide content	Percentage of pesticide in various particle size groups: > 150 µm Dry	> 150 µm Wet	75-149 µm Dry	75-149 µm Wet	45-74 µm Dry	45-74 µm Wet	< 44 µm Dry	< 44 µm Wet
A	4	Folpet 5%	1.3	0.3	3.0	9.3	12.3	45.0	83.2	45.3
B	6	Folpet 5%	1.6	0.1	12.3	1.8	30.5	13.1	54.7	84.6
C	3	Folpet 6.5%	2.3	0.1	15.1	2.2	33.5	14.9	45.7	82.8
D	2	Folpet 5%	3.6	0.1	36.0	3.1	29.4	6.8	31.0	90.1
E	3	Folpet 5%	5.5	0.6	30.0	1.2	50.0	5.7	14.6	92.5
F	3	Folpet 7.5%	22.4	0.3	52.9	2.4	17.8	5.2	7.0	92.1
G	1	Folpet 5%	14.2	0.1	33.7	1.5	47.0	5.2	5.1	93.2
H	1	Folpet 7.5% Sulfur 10%	6.1	2.7	16.5	2.3	56.6	8.5	20.8	86.5
I	11	Folpet 7.5% Sulfur 30%	26.2	0.1	56.4	2.9	10.6	7.0	5.0	90.0
J	2	Captan 5%	0.7	0.2	6.1	4.1	26.9	25.1	66.3	70.7
K	2	Captan 4%	39.5	0.2	41.7	2.1	12.2	16.5	6.7	82.2
L	3	Captan 5%	74.6	13.7	3.2	10.1	19.3	9.3	2.9	66.8
M	4	Captan 5% Sulfur 20%	15.2	2.3	42.1	2.3	24.2	7.5	18.5	87.9
N	2	Captan 4% Sulfur 25%	37.8	0.4	38.1	2.8	17.1	11.3	5.9	85.5
O	5	Captan 10% Sulfur 25%	12.3	1.0	70.1	4.0	12.1	20.0	5.3	75.0
P	2	Sulfur	0.7	17.2	1.2	6.1	19.3	16.7	78.9	60.1
Q	3	Karathane 0.9% Chlorothalonil 5%	1.4	0.1	15.0	1.0	33.5	6.6	50.2	92.3
R	3	Copper Zinc Chromate 89%	51.8	0.4	34.1	1.2	1.5	1.6	8.1	96.8
S	1	Zinc 3.9%	76.6	0.1	16.9	2.1	2.5	5.3	1.9	92.3

Literature Cited

1. American Society for Testing and Materials. 1969. Manual on Test Sieving Methods. ASTM Special Tech. Publ. 447. 43 pp.
2. CIPAC Handbook. 1970. Analysis of Technical and Formulated Pesticides. Collaborative International Pesticides Analytical Council Limited. W. Heffer and Sons Ltd., Cambridge, England. Vol. 1. 1079 pp.
3. Dooley, H. L. 1971. Application Characteristics of Plastic Squeeze and Pump Gun Type Garden Dusters. Plant Dis. Reptr. 55:1014-1017.
4. Lyle, E. W. 1943. Black-Spot on Rose Canes. Amer. Rose Annu. 28:155-156.
5. Massey, L. M. 1939. Fungicides for Roses. Amer. Rose Annu. 24:103-111.
6. Massey, L. M. 1946. Blackspot Can Be Controlled. Amer. Rose Annu. 31:111-119.
7. Meyer, L. J. 1930. Dusting Roses. Amer. Rose Annu. 15:79-81.
8. Robinson, R. H. 1922. The Physical Properties of Commercial Arsenates of Lead. The J. of Ind. and Eng. Chem. 14:311-317.
9. Streeter, L. R. 1927. Physical Properties of Commercial Dusting and Spraying Materials. N. Y. State Agr. Exp. Sta. Geneva Tech. Bull. 135. 12 pp.
10. Thatcher, R. W. and L. R. Streeter. 1925. The Adherence to Foliage of Sulfur in Fungicidal Dusts and Sprays. N. Y. State Agr. Exp. Sta. Geneva Tech. Bull. 116. 18 pp.